

**TECHNICAL SPECIFICATION (600x600mm)**

DESCRIPTION	NATIONAL STANDARD GB/T4100-2015 GB 6566-2010 HJ/T297-2006	TEST RESULTS	VERDICT
Water absorption (E)	AVG E≤0.5% INV E≤0.6%	AVG E≤0.09% INV E 0.05% ~ 0.12%	PASS
Breakage pressure (N)	When the thickness ≥ 7.5mm, the mean value shall not be less than 1300	1961	PASS
Modulus of breakage (Mpa)	AVG≥35Mpa INV≥32Mpa	AVG≥37Mpa INV 36~ 38Mpa	PASS
Resistance to household chemicals and swimming pool salts	Minimum GB	CLASS GA	PASS
Static coefficient of friction	≥0.50	Dry 0.59	PASS
Surface quality	A minimum of 95% of the tiles shall be free from visible defects that would impair the appearance of a major area of tiles.	Conformed	PASS
Thickness (%)	+_5%	+1.0% ~ +2.1%	PASS



	+_0.5mm		+0.1mm ~+0.2mm	
Rectangularity	+_0.15%	Max≤2.0mm	+0.02%~+0.05%	PASS
Surface flatness	+_0.14% Max≤2.0mm		-0.02%~+0.05%	PASS

PACKING DETAIL

SIZE MM (inch)	PCS/BOX	KGS/BOX	SQM/BOX	BOXES/PALLET (1.1X1.1M)	BOXES/21TON CONTAINER	BOXES/24TON CONTAINER	BOXES/27TON CONTAINER
600x1200 (24x48)	2	37.5	1.44	56	560	640	720
900x900 (36x36)	2	42.5	1.62	38	494	564	635
600x900 (24x36)	3	42.5	1.62	40	494	564	635
600x600 (24x24)	4	32	1.44	40	656	750	840
600x300 (24x12)	8	32	1.44	40	656	750	840
300x900 (12x6)	5	30	1.35	46	700	800	900