



TECHNICAL SPECIFICATION (600x600mm)

DESCRIPTION	NATIONAL STANDARD GB/T4100-2015 GB 6566-2010 HJ/T297-2006	TEST RESULTS	VERDICT
Water absorption (E)	AVG E≤0.5% INV E≤0.6%	AVG E≤0.05% INV E 0.04% ~0.07%	PASS
Breakage pressure (N)	When the thickness ≥ 7.5mm, the mean value shall not be less than 1300	2040	PASS
Modulus of breakage (Mpa)	AVG≥35Mpa INV≥32Mpa	AVG≥41Mpa INV 39~42Mpa	PASS
Resistance to household chemicals and swimming pool salts	Minimum GB	CLASS GA	PASS
Static coefficient of friction	≥0.5	Dry 0.68~ 0.69	PASS
Surface quality	A minimum of 95% of the tiles shall be free from visible defects that would impair the appearance of a major area of tiles.	Conformed	PASS
Thickness (%)	+_5% +_0.5mm	+1.0% ~+2.1% +0.1mm ~+0.2mm	PASS



Guangdong Xinruncheng Ceramics Co., Ltd.

Rectangularity	+ ₋ 0.5%	Max≤2.0mm	-0.05%~+0.07% -0.27~+0.43mm	PASS
Surface flatness	+ ₋ 0.5%Max≤2.0mm		-0.02%~+0.04% -0.19~+0.30mm	PASS

PACKING DETAIL

SIZE MM (inch)	PCS/BOX	KGS/BOX	SQM/BOX	BOXES/PALLET (1.1X1.1M)	BOXES/21TON CONTAINER	BOXES/24TON CONTAINER	BOXES/27TON CONTAINER
600x1200 (24x48)	2	37.5	1.44	56	560	640	720
900x900 (36x36)	2	42.5	1.62	38	494	564	635
600x900 (24x36)	3	42.5	1.62	40	494	564	635
600x600 (24x24)	4	32	1.44	40	656	750	840
600x300 (24x12)	8	32	1.44	40	656	750	840
300x900 (12x6)	5	30	1.35	46	700	800	900